PRODUCT DATA SHEET

08.02.2022 Ed. 3

Polypropylene
HJ120UB
Polypropylene Homopolymer

Description
HJ120UB is a special low viscosity polypropylene homopolymer developed to fit the production of fibre reinforced thermoplastics.

Applications
HJ120UB has been developed especially for applications like:

Under the bonnet components
Front end carriers
Dashboard carriers
Noise shields
Under body shieldings
Battery supports

Special Features
HJ120UB This material contains basic stabilisation.

Low emission

Physical Properties

Property	Typical Value Data should not be used for specification work	Test Method
Density	905 kg/m³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	75 g/10min	ISO 1133
Flexural Modulus (2 mm/min)	1.500 MPa	ISO 178
Tensile Strength (50 mm/min)	35 MPa	ISO 527-2
Heat Deflection Temperature B (0,45 MPa)	80 °C	ISO 75-2
Charpy Impact Strength, notched (23 °C)	1,0 kJ/m²	ISO 179/1eA

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

Processing Techniques
The actual conditions will depend on the type of equipment used.

HJ120UB is easy to process with standard direct LFT/injection moulding machines.To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 80°C.

Feeding temperature	40 - 80 °C	
Mass temperature	220 - 270 °C	for direct LFT compression or injection moulding
Holding pressure	30 - 60 bar	
Back pressure	Low to medium	
Mould temperature	30 - 60 °C	
Screw speed	Low to medium	
Flow front speed	100 - 200 m/min	

Storage
HJ120UB should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety
Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

Borealis AG | Trabrennstrasse 6-8 | 1020 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com

Manufacturer website: https://www.borealisgroup.com/

Polypropylene
HJ120UB

Recycling
The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of recovery and disposal of the product.

Regional Availability
Europe
For information on regional availability please contact Borealis Sales Representative.

Issuer:
Marketing Automotive / Daniel Bahls
Product Management / Ramesh Selvasankar

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

Borealis AG | Trabrennstrasse 6-8 | 1020 Vienna | Austria
Telephone +43 1 224 00 0 | Fax +43 1 22 400 333
FN 269858a | CCC Commercial Court of Vienna | Website www.borealisgroup.com