Braskem

Datasheet
21/02/2020

High Density Polyethylene HD7000C

Description:

HD7000C is a high density polyethylene, homopolymer designed for blow-molding segment. HD7000C shows high stiffness properties, good impact resistance, good surface quality and good organoleptic properties.

Applications:

Containers for food products, toys, Blow molding small volumes, Juice packaging, bottles for ethylic alcohol, Food packaging, Dairy based products packaging

Processes:

Injection blow molding, Extrusion Blow Molding

Control Properties:

Feature	Method	Units	Values
Melt Flow Rate (190°C/2.16kg)	D 1238	g/10 min	0.35
Density	D 792	g/cm³	0.963

Typical Properties:

Plaque Properties

Feature	Method	Units	Values
Melt Flow Rate (190°C/21,6kg)	ASTM D 1238	g/ 10 min	32
Tensile Strength at Yield (a)	D 638	MPa	30
Tensile Strength at Break (a)	D 638	MPa	30
Flexural Modulus - 1% Secant (b)	D 790	MPa	1600
Tensile Impact Strength ISO at 23 °C	ISO 8256	kJ/m²	90
Deflection Temperature under Load at 0.455 MPa (b)	D 648	°C	75

Typical properties correspond to average values obtained in our laboratories. Test specimens prepared from compression molded sheet made according to ASTM D 4703. Thickness of test piece: a) 2 mm; b) 3 mm.

Final Remarks

1. It is the sole responsibility of the Client/Purchaser of this Product to verify the suitability of this Product and its use for the intended use and to ensure compliance with legal and regulatory requirements applicable to the final product.
2. The technical guidance eventually rendered to the Client/Purchaser of the Product by Braskem about the Product does not characterize a performance guarantee for the intended application, nor does it exempt the Client/Purchaser from the responsibilities described in item 1 above.
3. Any application information about the Product does not mean that Braskem knows or has validated the productive process of the Client/Purchaser or the adequacy of the Product for the intended application. All warranties of merchantability or fitness for a particular purpose, express or implied, are expressly excluded.
4. The information provided herein is of the date hereof and Braskem may update, revise or amend the information contained herein at any time and without previous notice. The Client/Purchaser shall consult www.braskem.com to verify any updates to this information.
5. For regulatory information associated with the Product and its source, please consult the Regulatory Information Sheet (RIS). For other requests, please contact Braskem's Technical Services area.
6. The information contained herein is provided based on the best of Braskem's knowledge, indicating typical values of the properties of the Product, and such values shall not be considered absolute or as a guarantee.