Braskem I'm green BIO-BASED

Data Sheet
17/01/2019

Low Density Polyethylene SBC818

Description:

SBC818 is a low density polyethylene developed for coating process, it presents very good optical properties, low neck-in, good film stability, and good adhesion on porous substrate. Additives free. The minimum carbon biobased content of this grade is 95%, determined according to ASTM D6866.

Aplicações:

General use articles, Specialty Film - Extrusion Coating, Masterbatches

Processos:

Extrusion Coating

Control Properties:

Característica	Método	Unidades	Valores
Melt Flow Rate (190°C/2.16kg)	D 1238	g/10 min	8.3
Density	D 1505	g/cm³	0.918

Typical Properties - Films:

Blow film Properties (a)

Característica	Método	Unidades	Valores
Tensile Strength at Break (MD/TD)	D 882	MPa	25/20
Elongation at Break (MD/TD)	D 882	%	380/870
Dart Drop Impact	D 1709	g/F50	70
Elmendorf Tear Strength (MD/TD)	D 1922	gF	ND(b)/56
Haze	D 1003	%	8
Gloss - Angle 60°	D 2457	%	76

(a) LDPE: 25 µm thick film, obtained from a 75 mm extruder, with blow up ratio of 2:1, die gap 1 mm and Die rate 1,75 kg/h.cm (MD = Machine Direction and TD = Transversal Direction). (b) ND: Not Determined. (c) 25 µm thick film, temperature: 38° C, 100% RH.

Final Remarks

1. It is the sole responsibility of the Client/Purchaser of this Product to verify the suitability of this Product and its use for the intended use and to ensure compliance with legal and regulatory requirements applicable to the final product.
2. The technical guidance eventually rendered to the Client/Purchaser of the Product by Braskem about the Product does not characterize a performance guarantee for the intended application, nor does it exempt the Client/Purchaser from the responsibilities described in item 1 above.
3. Any application information about the Product does not mean that Braskem knows or has validated the productive process of the Client/Purchaser or the adequacy of the Product for the intended application. All warranties of merchantability or fitness for a particular purpose, express or implied, are expressly excluded.
4. The information provided herein is of the date hereof and Braskem may update, revise or amend the information contained herein at any time and without previous notice. The Client/Purchaser shall consult www.braskem.com to verify any updates to this information.
5. For regulatory information associated with the Product and its source, please consult the Regulatory Information Sheet (RIS). For other requests, please contact Braskem's Technical Services area.
6. The information contained herein is provided based on the best of Braskem's knowledge, indicating typical values of the properties of the Product, and such values shall not be considered absolute or as a guarantee.