Braskem I'm green BIO-BASED

Data Sheet
30/03/2020

Low Density Polyethylene SPB208

Description:

SPB208 is a low density polyethylene designed for injection molding. This grade shows excellent processability being indicated for applications where low viscosity is required during processing. Injection molded products with this resin shows good flexibility. Additives free. The minimum carbon biobased content of this grade is 95%, determined according to ASTM D6866.

Aplicações:

Masterbatches, Caps

Processos:

Injection molding

Control Properties:

Característica	Método	Unidades	Valores
Melt Flow Rate (190°C/2.16kg)	D 1238	g/10 min	22
Density	D 1505	g/cm³	0.923

Typical Properties - Plaque[1]:

Plaque Properties

Característica	Método	Unidades	Valores
Tensile Strength at Yield (a)	D 638	MPa	10
Tensile Strength at Break (a)	D 638	MPa	8
Elongation at Break (a)	D 638	%	139
Flexural Modulus - 2% Secant (b)	D 790	MPa	250
Hardness (c)	D 2240	-	45
Vicat Softening Temperature at 10 N (b)	D 1525	°C	87

[1] Test specimens from compression molded plaque according to ASTM D4703. Plaque Thickness: a) 2mm. b) 3mm c) 6mm. NB = No break.

Final Remarks

1. It is the sole responsibility of the Client/Purchaser of this Product to verify the suitability of this Product and its use for the intended use and to ensure compliance with legal and regulatory requirements applicable to the final product.
2. The technical guidance eventually rendered to the Client/Purchaser of the Product by Braskem about the Product does not characterize a performance guarantee for the intended application, nor does it exempt the Client/Purchaser from the responsibilities described in item 1 above.
3. Any application information about the Product does not mean that Braskem knows or has validated the productive process of the Client/Purchaser or the adequacy of the Product for the intended application. All warranties of merchantability or fitness for a particular purpose, express or implied, are expressly excluded.
4. The information provided herein is of the date hereof and Braskem may update, revise or amend the information contained herein at any time and without previous notice. The Client/Purchaser shall consult www.braskem.com to verify any updates to this information.
5. For regulatory information associated with the Product and its source, please consult the Regulatory Information Sheet (RIS). For other requests, please contact Braskem's Technical Services area.
6. The information contained herein is provided based on the best of Braskem's knowledge, indicating typical values of the properties of the Product, and such values shall not be considered absolute or as a guarantee.