Datasheet
07/06/2026

Linear Low Density Polyethylene SLH218

Description:

SLH218 is an ethylene alpha-olefin copolymer with a density lower than 0.94, produced by Braskem. It shows a good balance between optical properties, mechanical properties (Mainly stretchability), sealability and processability. Very low gel contained. The minimum biobased carbon content of this grade is 84%, determined according to ASTM D6866.

Applications:

Blends with HDPE, Stretch Films, Medium voltage XLPE insulation, Liners, Flexible Packaging (Cast Films)., Blends with LDPE, General use packing, Blends for irrigation pipes, Low voltage XLPE insulation, Wire insulation

Processes:

Cast Film Extrusion., Blown Film Extrusion

Control Properties:

Feature	Method	Units	Values
Melt Flow Rate (190°C/2.16kg)	D 1238	g/10 min	2.3
Density	D 1505	g/cm³	0.916

Typical Properties - Films:

Blown Film Properties

Feature	Method	Units	Values
Highlight - Ultimate Test (1)(2)	D 4649	%	400
Highlight - Puncture (1)(2)	D 4649	kg	2.6
Highlight - Retention Maximum Force (1)(2)	D 4649	kg	3.1
Highlight - Retention Ending Force (1)(2)	D 4649	kg	2
Highlight - Retention Loss (1)(2)	D 4649	%	35
Highlight - Cling (1)(2)	D 4649	g	29
Highlight - Unwind Force (1)(2)	D 4649	kgf	3.7
Highlight - Sond level (1)(2)	D 4649	dB	73
Highlight - Elongation Force (1)(2)	D 4649	kgf	34
Haze	D 1003	%	3
Gloss - Angle 45º	D 2457	%	95

(1) 23µm thickness film, processed in a 3 layer coextruder (2) Highlight tested at 300%

Typical Properties - Films:

Blown Film Propertiesª

Feature	Method	Units	Values
Tensile Strength at Break (MD/TD)	D 882	MPa	40/40
Elongation at Break (MD/TD)	D 882	%	1170/1500
Tensile Modulus - 1% Secant (MD/TD)	D 882	MPa	210/240
Dart Drop Impact	D 1709	g/F50	110
Elmendorf Tear Strength (MD/TD)	D 1922	gF	240/520

(a) Film with 38 microns produce in a 40mm extruder and a blow-up ratio of 2.2:1. (MD = extrusion direction and TD = transversal direction).

Final Remarks

1. It is the sole responsibility of the Client/Purchaser of this Product to verify the suitability of this Product and its use for the intended use and to ensure compliance with legal and regulatory requirements applicable to the final product.
2. The technical guidance eventually rendered to the Client/Purchaser of the Product by Braskem about the Product does not characterize a performance guarantee for the intended application, nor does it exempt the Client/Purchaser from the responsibilities described in item 1 above.
3. Any application information about the Product does not mean that Braskem knows or has validated the productive process

of the Client/Purchaser or the adequacy of the Product for the intended application. All warranties of merchantability or fitness for a particular purpose, express or implied, are expressly excluded.

4. The information provided herein is of the date hereof and Braskem may update, revise or amend the information contained herein at any time and without previous notice. The Client/Purchaser shall consult www.braskem.com to verify any updates to this information.
5. For regulatory information associated with the Product and its source, please consult the Regulatory Information Sheet (RIS). For other requests, please contact Braskem's Technical Services area.
6. The information contained herein is provided based on the best of Braskem's knowledge, indicating typical values of the properties of the Product, and such values shall not be considered absolute or as a guarantee.