Braskem

Datasheet
03/2026

Polypropylene DC7056.05

Description:

BRASKEM Polypropylene DC7056.05 is an Impact Copolymer developed for film-extrusion, sheet-extrusion and injection molding applications. BRASKEM Polypropylene DC7056.05 combines very good processability with exceptional impact strength and high stffness level.

Applications:

Furniture, Flexible packaging., household items

Processes:

Film Extrusion, Thermoforming, Injection molding

Typical Properties[a]

Feature	Method	Units	Values
Melt Flow Rate (230°C/2.16 kg)	ISO 1133	g/10 min	3.5
Density	ISO 1183-1	g/cm³	0.900
Flexural Modulus [a]	ISO 178	MPa	1000
Tensile Strength at Yield [a]	ISO 527-1	MPa	24
Tensile Elongation at Yield [a]	ISO 527-1	%	9
Notched Charpy Impact Strength at 23°C [a]	ISO 179	kJ/m²	14
Notched Charpy Impact Strength at 0°C [a]	ISO 179	kJ/m²	7
Notched Charpy Impact Strength at -20°C [a]	ISO 179	kJ/m²	4
Heat Deflection Temperature under Load at 0.455 MPa [a]	ISO 75-1/75-2	°C	76
Vicat Softening Temperature at 10 N [a]	ISO 306	°C	158

a) Injection molded specimen according to ISO 294.

-

1. **Storage:**
   Recommended storage is a cool, dry place protected from direct sunlight. High temperatures and high atmospheric humidity during storage may have an impact on product performance.

2. **Disclaimer:**
   - Braskem Netherlands B.V. or any of its affiliates assumes no liability on the suitability of the product as described in this document for any intended use in any application unless separately agreed in a contract. All warranties or merchantability or fitness for a particular purpose are expressly excluded.
   - Braskem Netherlands B.V. does not support the use of the product as described in this document in any medical application regardless of the Medical Device Regulation (2017/745). The use of this product into any medical applications regardless of classification or intended use, requires written approval from Braskem Netherlands B.V..
   - Braskem Netherlands B.V. assumes no obligation or liability for the information provided in this document.

3. **Customer Notice:**
   Braskem strongly encourages its customers to review both their manufacturing processes and their applications of Braskem products from a human health and environmental quality standpoint to ensure that Braskem products are not used in ways that are not intended or tested. Braskem product literature, including Safety Data Sheets, should be consulted prior to using Braskem products.

   - Current Safety Data Sheets are available from Braskem.
   - Braskem Netherlands B.V. strongly recommends before use, to consult the Safety Data Sheet.

   For regulatory information, please contact polymer.compliance-europe@braskem.com