Braskem

Datasheet
Review 5 (Feb / 18)

Polypropylene H 201

Description:

Homopolymer

H 201 is a high melt flow rate additivated homopolymer suitable for injection molding and fiber extrusion applications. This product exhibits excellent processability with good melt stability and stiffness/impact strength balance. It also features low taste/odor transfer.

Applications:

Home appliances, Nonwovens, Continuous filament for ropes, Continuous filament for sewing thread, Continuous filament for carpets, Drawers, staple fiber needle punched carpets

Processes:

Fiber Extrusion, Injection molding

Control Properties

Feature	Method	Units	Values
Melt Flow Rate (230°C/2.16 kg)	D 1238	g/10 min	20

Typical Properties

Feature	Method	Units	Values
Density	D 792	g/cm³	0.905
Flexural Modulus - 1% Secant	D 790	MPa	1400
Tensile Strength at Yield	D 638	MPa	35
Tensile Elongation at Yield	D 638	%	10
Rockwell Hardness (R Scale)	D 785	-	100
Notched Izod Impact Strength at 23°C	D 256	J/m	20
Deflection Temperature under Load at 0.455 MPa	D 648	°C	110
Deflection Temperature under Load at 1.820 MPa	D 648	°C	57
Vicat Softening Temperature at 10 N	D 1525	°C	154

a) Injection molded specimen according to ASTM D 4101. NB = No Break.

Final Remarks

1. The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
2. In some applications, Braskem has developed tailor-made resins to reach specific requirements.
3. In case of doubt regarding utilization, or for other applications, please contact our Technical Assistance.
4. For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS.
5. For regulatory information concerning the product, please consult the Regulatory Information Sheet or contact our Technical Assistance Area.
6. The mentioned values in this report can be changed at any moment without Braskem previous communication.