Braskem

Datasheet
Review 5 (May / 18)

Polypropylene PH 0130

Description:
Homopolymer

PH 0130 is a low melt flow rate additivated homopolymer used for general purposes. This resin is designed for blow moulding and extrusion. PH 0130 features excellent processability and stiffness/impact strength balance.

Applications:
Profiles, Ropes, Bottles for mineral water, juices, cosmetics and general uses, Flat and corrugated sheets, Tear tape, Tapes in general

Processes:
Extrusion Blow Molding, General extrusion.

Control Properties

Feature	Method	Units	Values
Melt Flow Rate (230°C/2.16 kg)	D 1238	g/10 min	1.2

Typical Properties

Feature	Method	Units	Values
Density	D 792	g/cm³	0.905
Flexural Modulus - 1% Secant	D 790	MPa	1300
Tensile Strength at Yield	D 638	MPa	36
Tensile Elongation at Yield	D 638	%	10
Rockwell Hardness (R Scale)	D 785	-	98
Notched Izod Impact Strength at 23°C	D 256	J/m	45
Deflection Temperature under Load at 0.455 MPa	D 648	°C	92
Vicat Softening Temperature at 10 N	D 1525	°C	156

a) Injection molded specimen according to ASTM D 4101. NB = No Break.

Final Remarks

1. The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
2. In some applications, Braskem has developed tailor-made resins to reach specific requirements.
3. In case of doubt regarding utilization, or for other applications, please contact our Technical Assistance.
4. For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS.
5. For regulatory information concerning the product, please consult the Regulatory Information Sheet or contact our Technical Assistance Area.
6. The mentioned values in this report can be changed at any moment without Braskem previous communication.