Braskem

Datasheet
Review 5 (Jan / 18)

Polypropylene PH 0952

Description:
Homopolymer

PH 0952 is a medium melt flow rate homopolymer, with slip and antiblocking agents. This product is designed for technical films segment and packaging for cast and blown film extrusion. This product features excellent optical properties and good processability.

Applications:
Very thin film on high-speed line, low thickness., Food packaging, Films for lamination, roll films for automatic packaging, Textile Applications

Processes:
Cast Film Extrusion., Blown Film Extrusion

Control Properties

Feature	Method	Units	Values
Nominal Melt Flow (230°C/2.16kg)	D 1238	g/10 min	8.0

Typical Properties[a]

Feature	Method	Units	Values
Density	D 792	g/cm³	0.905
Flexural Modulus (0.05 in/min, 1.3 mm/min, 1% secant)	D 790	MPa	1200
Tensile Strength at Yield (2 in/min, 50 mm/min)	D 638	MPa	35
Elongation at Yield (2 in/min, 50 mm/min)	D 638	%	11
Rockwell Hardness (R Scale)	D 785	-	90
Notched Izod Impact Strength (at 23°C)	D 256	J/m	30
Heat Deflection Temperature (0.45 Mpa)	D 648	°C	95
Deflection Temperature under Load at 1.820 MPa	D 648	°C	55
Vicat Softening Temperature (at 10 N)	D 1525	°C	149

a) Injection molded specimen according to ASTM D 4101. NB = No Break.

Film Properties

Feature	Method	Units	Values
Secant Modulus 1% (MD/TD)	D 882	MPa	600/620
Tensile Strength at Yield (MD/TD)	D 882	MPa	23/23
Elongation at Yield (MD/TD)	D 882	%	11/10
Haze	D 1003	%	2.5
Gloss 45°	D 2457	-	93
Sealing Initial Temperature	Braskem Method	ºC	115

3) 30 µm thickness film, processed in a 50 mm screw diameter extruder with blow up ratio of 1,3:1 (MD=Machine Direction and TD=Transversal Direction)

Final Remarks

1. It is the sole responsibility of the Client/Purchaser of this Product to verify the suitability of this Product and its use for the intended use and to ensure compliance with legal and regulatory requirements applicable to the final product.
2. The technical guidance eventually rendered to the Client/Purchaser of the Product by Braskem about the Product does not characterize a performance guarantee for the intended application, nor does it exempt the Client/Purchaser from the responsibilities described in item 1 above.
3. Any application information about the Product does not mean that Braskem knows or has validated the productive process of the Client/Purchaser or the adequacy of the Product for the intended application. All warranties of merchantability or fitness for a particular purpose, express or implied, are expressly excluded.
4. The information provided herein is of the date hereof and Braskem may update, revise or amend the information contained herein at any time and without previous notice. The Client/Purchaser shall consult www.braskem.com to verify any updates to this information.
5. For regulatory information associated with the Product and its source, please consult the Regulatory Information Sheet

(RIS). For other requests, please contact Braskem's Technical Services area.

6. The information contained herein is provided based on the best of Braskem's knowledge, indicating typical values of the properties of the Product, and such values shall not be considered absolute or as a guarantee.