Product Datasheet

ExxonMobil Signature Polymers

ExxonMobil™ LD 3034 Series

Low Density Polyethylene

Product Description

ExxonMobil™ LD 3034 series LDPE grades offer an excellent combination ofhigh clarity with high stiffness. Several additive packages are available according to the required surface properties.

General

Availability [1]	▪ Africa & Middle East	▪ Asia Pacific	▪ Europe
Additive	▪ LD 3034.BW: Antiblock: No; Slip: No; Thermal Stabilizer: Yes ▪ LD 3034.GZ: Antiblock: 1000 ppm; Slip: 1050 ppm; Thermal Stabilizer: Yes ▪ LD 3034.HR: Antiblock: 400 ppm; Slip: 650 ppm; Thermal Stabilizer: Yes		
Applications	▪ Cast Film ▪ Co-Extrusion Films ▪ Embossed Film	▪ Hygiene Packaging ▪ Label Film ▪ Overwrap Film	▪ Paper Overwrap
Revision Date	▪ 11/01/2013		

Resin Properties	Typical Value (English)		Typical Value (SI)		Test Based On
Density	0.934	g/cm³	0.934	g/cm³	ASTM D1505
Melt Index (190°C/2.16 kg)	3.0	g/10 min	3.0	g/10 min	ASTM D1238
Peak Melting Temperature	241	°F	116	°C	ExxonMobil Method

Film Properties	Typical Value (English)		Typical Value (SI)		Test Based On
Tensile Strength at Yield TD	2200	psi	15	MPa	ASTM D882
Tensile Strength at Break MD	3200	psi	22	MPa	ASTM D882
Tensile Strength at Break TD	2600	psi	18	MPa	ASTM D882
Elongation at Break MD	430	%	430	%	ASTM D882
Elongation at Break TD	560	%	560	%	ASTM D882
Secant Modulus MD - 1% Secant	54000	psi	370	MPa	ASTM D882
Secant Modulus TD - 1% Secant	54000	psi	370	MPa	ASTM D882
Dart Drop Impact	60	g	60	g	ASTM D1709A
Elmendorf Tear Strength MD	100	g	100	g	ASTM D1922
Elmendorf Tear Strength TD	170	g	170	g	ASTM D1922

Optical Properties	Typical Value (English)		Typical Value (SI)		Test Based On
Gloss (45°)	73		73		ASTM D2457
Haze	6.0	%	6.0	%	ASTM D1003

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

The test specimen were prepared on LD 3034.BW, 30µm (1.18mil) thick film, using a 200 mm (7.9 in) die, die gap of 1.0 mm (39.4 mil), Blow-Up Ratio of 2.5 and temperature profile of 140 - 170°C (284 - 338°F).

Notes

Typical properties: these are not to be construed as specifications.

[1] Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Manufacturer website: https://www.exxonmobilchemical.com/en/products/polyethylene

Product Datasheet

ExxonMobil™ LD 3034 Series
Low Density Polyethylene

For additional technical, sales and order assistance: Contact Us

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com