Product Datasheet

ExxonMobil Signature Polymers

Exceed™ m 4518.CB Wire & Cable

Metallocene Polyethylene

Product Description

Exceed™ m 4518.CB performance polymer resin is an ethylene 1-hexene copolymer. It is an excellent blend partner in halogen-free flame retardant compounds and cable jacketing to balance inherent mechanical strength with good processability. It has superior mechanical properties that protect cables in various working conditions. Sufficient carbon black or UV stabilizer should be added to meet cable jacketing specifications.

General

Availability [1]	▪ Latin America	▪ North America	
Additive	▪ Thermal Stabilizer: Yes		
Applications	▪ Communication Cable ▪ Halogen-free flame retardant (HFFR) compounds	▪ High Voltage Jacketing ▪ Low Voltage Jacketing	▪ Medium Voltage Jacketing
Form(s)	▪ Pellets		
Revision Date	▪ 04/01/2019		

Resin Properties	Typical Value	(English)	Typical Value	(SI)	Test Based On
Density / Specific Gravity	0.918	g/cm³	0.918	g/cm³	ASTM D792
Melt Index (190°C/2.16 kg)	4.5	g/10 min	4.5	g/10 min	ASTM D1238
Peak Melting Temperature	235	°F	113	°C	ExxonMobil Method

Thermal	Typical Value	(English)	Typical Value	(SI)	Test Based On
Vicat Softening Temperature	217	°F	103	°C	ASTM D1525

Molded Properties	Typical Value	(English)	Typical Value	(SI)	Test Based On
Tensile Strength at Yield					ASTM D638
20 in/min (510 mm/min)	1700	psi	12	MPa	
Tensile Strength at Break					ASTM D638
20 in/min (510 mm/min)	4100	psi	29	MPa	
Elongation at Yield (20 in/min (510 mm/min))	10	%	10	%	ASTM D638
Elongation at Break (20 in/min (510 mm/min))	730	%	730	%	ASTM D638
Flexural Modulus - 1% Secant (0.051 in/min (1.3 mm/min))	33000	psi	230	MPa	ASTM D790A
Durometer Hardness (Shore D, 15 sec)	48		48		ASTM D2240

Electrical	Typical Value	(English)	Typical Value	(SI)	Test Based On
Volume Resistivity (500 V)	6.4E+14	ohms·m	6.4E+14	ohms·m	IEC 62631-3-1
Relative Permittivity (1 MHz)	2.28		2.28		IEC 62631-2-1
Dissipation Factor (1 MHz)	1.7E-4		1.7E-4		IEC 62631-2-1

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Specimens were compression molded in accordance with ASTM D 4703, Procedure C.

Notes

Typical properties: these are not to be construed as specifications.

[1] Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Manufacturer website: https://www.exxonmobilchemical.com/en/products/polyethylene

Product Datasheet

ExxonMobil

Exceed™ m 4518.CB Wire & Cable
Metallocene Polyethylene

For additional technical, sales and order assistance: Contact Us

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com