Manufacturer website: https://www.exxonmobilchemical.com/en/products/polyethylene

Product Datasheet

ExxonMobil Signature Polymers

Exceed™ Flow PP7905E1

Polypropylene Impact Copolymer

Product Description

A high crystallinity, low impact strength copolymer resin designed for compounding base or injection molding applications requiring very high melt flow rate.

General

Availability [1]	▪ Latin America	▪ North America	
Features	▪ High Flow	▪ High Stiffness	▪ Nucleated
Uses	▪ Automotive Applications	▪ Compounding	
Appearance	▪ Natural Color		
Form(s)	▪ Pellets		
Processing Method	▪ Injection Molding		
Revision Date	▪ 12/01/2017		

Physical	Typical Value (English)		Typical Value (SI)		Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	100	g/10 min	100	g/10 min	ASTM D1238
Density	0.900	g/cm³	0.900	g/cm³	ExxonMobil Method

Mechanical	Typical Value (English)		Typical Value (SI)		Test Based On
Tensile Strength at Break	4870	psi	33.6	MPa	ASTM D638
Tensile Stress at Break	4640	psi	32.0	MPa	ISO 527-2/50
Elongation at Break	3.8	%	3.8	%	ASTM D638
Tensile Strain at Break	4.3	%	4.3	%	ISO 527-2/50
Flexural Modulus - 1% Secant					
0.051 in/min (1.3 mm/min)	272000	psi	1880	MPa	ASTM D790A
0.51 in/min (13 mm/min)	307000	psi	2120	MPa	ASTM D790B
Flexural Modulus (0.079 in/min (2.0 mm/min))	264000	psi	1820	MPa	ISO 178

Impact	Typical Value (English)		Typical Value (SI)		Test Based On
Notched Izod Impact					ASTM D256A
0°F (-18°C)	0.45	ft·lb/in	24	J/m	
73°F (23°C)	0.66	ft·lb/in	35	J/m	
Notched Izod Impact Strength					ISO 180/1A
-40°F (-40°C)	1.1	ft·lb/in²	2.4	kJ/m²	
-4°F (-20°C)	1.2	ft·lb/in²	2.5	kJ/m²	
73°F (23°C)	2.2	ft·lb/in²	4.7	kJ/m²	
Charpy Notched Impact Strength					ISO 179/1eA
-22°F (-30°C)	0.67	ft·lb/in²	1.4	kJ/m²	
-4°F (-20°C)	0.81	ft·lb/in²	1.7	kJ/m²	
32°F (0°C)	1.2	ft·lb/in²	2.5	kJ/m²	
73°F (23°C)	2.5	ft·lb/in²	5.3	kJ/m²	
Gardner Impact					ASTM D5420
-20°F (-29°C), 0.125 in (3.18 mm), Geometry GC	< 8.00	in·lb	< 0.904	J	

Thermal	Typical Value (English)		Typical Value (SI)		Test Based On
Heat Deflection Temperature (1.80 MPa)	139	°F	59.4	°C	ISO 75-2/Af
Heat Deflection Temperature (0.45 MPa)	243	°F	117	°C	ISO 75-2/Bf
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	256	°F	125	°C	ASTM D648
DTUL (66 psi) - Annealed	264	°F	129	°C	ASTM D648

Hardness	Typical Value (English)		Typical Value (SI)		Test Based On
Rockwell Hardness	110		110		ASTM D785

Manufacturer website: https://www.exxonmobilchemical.com/en/products/polyethylene

ExxonMobil

Exceed™ Flow PP7905E1
Polypropylene Impact Copolymer

Additional Information

ASTM D638 & ISO 527-2/50: No Yield

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Notes

Typical properties: these are not to be construed as specifications.

[1] Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance: Contact Us

©2025 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Product Solutions" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Product Solutions Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

exxonmobilchemical.com