TECHNICAL DATA SHEET

HYOSUNG Polypropylene
The Next Circular Economy

HB240P

Block Copolymer

For Sewage and Drainage Pipes

Product Description

HYOSUNG Polypropylene HB240P is specially designed polypropylene block copolymer that features good stiffness. It is suitable for non-pressure pipes including sewage and drainage pipes and fittings. **PP HB240P** complies with regulation ISO/DIS 15874 hydrostatic pressure requirements and GB/T 17219-1998 for drinking water system.

Application

Sewage and drainage pipes
(Solid and double wall pipes)
Fittings for sewage and drainage pipes

Features

Good stiffness
Excellent surface property

Properties

Properties	Test Method	Typical Value	Unit
Resin Properties			
Melt Index(230℃, 2.16kg)	ASTM D1238	0.35	g/10min
Density	ASTM D792	0.90	g/cm^3
Mechanical Properties			
Tensile Strength at Yield	ASTM D638	320	kg/cm^2
Flexural Modulus	ASTM D790	15,500	kg/cm^2
Izod Impact Strength, Notched at 23℃	ASTM D256	N.B	kg·cm/cm
Izod Impact Strength, Notched at -10℃	ASTM D256	9.0	kg·cm/cm
Rockwell Hardness	ASTM D785	90	R-Scale
Heat Deflection Temperature (0.45MPa)	ASTM D648	110	℃
VICAT Softening Temperature (10N)	ASTM D1525	150	℃

* The values listed above are typical values for reference purpose only and shall not be construed as specifications.

Storage and Handling

This product should be stored in dry condition at temperature below 40˚C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: 80~100℃ / 2~4hours at air circulated condition)

Disclaimer

All information, including product characteristics, applications and properties are for reference purpose only and shall not be construed as specifications. Before using this product, customers should carefully review the instructions for use of the product to determine whether the product is suitable for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of this product. HYOSUNG CHEMICAL CORPORATION assumes no legal responsibility or liability for the contents of this document. We reserve the right to change the contents of this document without prior notice. This document is copyrighted by HYOSUNG CHEMICAL CORPORATION.

Contacts

Head Office (06578) 235, Banpo-daero, Seocho-gu, Seoul, KR
Tel: +82-2-2146-5439
Online www.hyosungchemical.com

HYOSUNG CHEMICAL


TECHNICAL DATA SHEET

HYOSUNG Polypropylene
The Next Circular Economy

HB240P

Block Copolymer
For Sewage and Drainage Pipes

Processing Parameters



Specifications	Unit	Recommended Parameters
Feed Zone Temperature	℃	170 ~ 190
Melting Zone Temperature	℃	190 ~ 225
Metering Zone Temperature	℃	200 ~ 235
Die or Nozzle Temperature	℃	200 ~ 235
Screw Speed	rpm	20 ~ 30

Considerations
Due to variations in screw design and heat efficiency according to types of facilities, optimal conditions for each facility may differ. Therefore, the optimal temperature conditions for each facility must be taken into consideration depending on thickness of final products, extruding pressure, cooling efficiency, changes in MI of the final product, appearances of the final product, and others.

Compliance

The pipes produced with **PP HB240P** comply with the hydrostatic pressure requirements according to ISO/DIS 15874 and GB/T 17219-1998 for drinking water system.
It complies with the requirements of FDA 21 CFR 177.1520 and European Commission Regulation (EU) No 10/2011 and its amendments up to (EU) No 2023/1627 with regard to plastic materials and articles intended to come into contact with food.

Contacts

Head Office (06578) 235, Banpo-daero, Seocho-gu, Seoul, KR
Tel: +82-2-2146-5439
Online www.hyosungchemical.com

HYOSUNG CHEMICAL