T50-200-178 Polyethylene Copolymer

T50-200-178 is a high density polyethylene copolymer with narrow molecular weight distribution. It is intended for injection molding applications which require high impact resistance and good environmental stress crack resistance. This material meets the Food and Drug Administration requirements of 21 CFR 177.1520.

Typical Properties[1]

	Values		ASTM
	English Units	SI Units	Method
Resin			
Density	–	0.9520 g/cc	**D4883**
Melt Index 190 C/2.16 kg	–	2.00 g/10 min	**D1238**
Compression Molded Sample			
Tensile Strength (2 in/min)			**D638**
@ Yield	4,000 psi	27.5 MPa	
@ Break	5,100 psi	35.0 MPa	
Elongation (2 in/min)			**D638**
@ Yield	9.1 %	9.1 %	
@ Break	1355 %	1355 %	
Flexural Modulus			**D790A**
Tangent Method	178,700 psi	1,230 MPa	
Notched Izod Impact Strength	2.16 ft-lbf/in	11.31 kJ/m^2	**D256**
Hardness			**D2240**
Shore D	68	68	
Vicat Softening Point	262 F	128 C	**D1525**
Brittleness Temperature	<-94 F	<-70 C	**D746**
Heat Deflection Temperature			**D648**
@ 66 psi (455 kPa)	160 F	71 C	
Environmental Stress Crack Resistance			**D1693**
Condition B, 100% Igepal F50 (hrs.)	16.5	16.5	

[1] **Typical properties will vary and are not to be used for specification purposes.**

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. As conditions of use may vary and are beyond the control of INEOS Olefins & Polymers USA, no representations or warranty, express or implied, are made with respect to the accuracy, reliability, or completeness of this information. This information in no way modifies, amends, enlarges, or creates any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE HEREBY EXCLUDED. INEOS Olefins & Polymers USA shall not be responsible for any damage or injury resulting from abnormal use, from any failure to follow appropriate practices, or from hazards inherent in the nature of the product and/or material, nor for toxicological effects or Industrial Hygiene associated with particular use of any product described herein. This information relates only to the specific product and/or material designated and may not be valid for such product and/or material used in combination with any other product and/or material or in any process, unless otherwise specified. This information shall not be construed as a recommendation for any use that may infringe any patent, trademark, or the like, or as an endorsement of any material, equipment, service, or other item not supplied by INEOS Olefins & Polymers USA.

The name and logo INEOS are trademarks of the INEOS Group and its affiliated companies and businesses.

2600 South Shore Boulevard, Ste. 500
League City, TX 77573
Tel: 281-535-6600
www.ineos-op.com

INEOS Olefins & Polymers USA

Manufacturer website: https://www.ineos.com/businesses/ineos-olefins-polymers/

T50-200-178 Polyethylene Copolymer

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices; for further information, call + 1-800-527-5419.

Health and Safety Information

The product described herein may require precautions in handling and use because of toxicity, flammability, or other consideration. The Material Safety Data Sheet (MSDS) contains the available product health and safety information for this material and can be found at **www.ineos-op.com**. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

The Material Safety Data Sheet for this product contains shipping descriptions and should be consulted, before transportation, as a reference in determining the proper shipping description. If the material shipped by INEOS is altered or modified, different shipping descriptions may apply and the MSDS of the original material should not be used.

For additional information, samples, pricing and availability, please contact:

INEOS Olefins & Polymers, USA
Marina View Building
2600 South Shore Boulevard
Suite 500
League City, Texas 77573
Phone: +1 281 535 6600
Fax: +1 281 535 6764
Customer Service: +1 800 527 5419
Tech Service: +1 800 338 0489
www.ineos-op.com

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. As conditions of use may vary and are beyond the control of INEOS Olefins & Polymers USA, no representations or warranty, express or implied, are made with respect to the accuracy, reliability, or completeness of this information. This information in no way modifies, amends, enlarges, or creates any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE HEREBY EXCLUDED. INEOS Olefins & Polymers USA shall not be responsible for any damage or injury resulting from abnormal use, from any failure to follow appropriate practices, or from hazards inherent in the nature of the product and/or material, nor for toxicological effects or Industrial Hygiene associated with particular use of any product described herein. This information relates only to the specific product and/or material designated and may not be valid for such product and/or material used in combination with any other product and/or material or in any process, unless otherwise specified. This information shall not be construed as a recommendation for any use that may infringe any patent, trademark, or the like, or as an endorsement of any material, equipment, service, or other item not supplied by INEOS Olefins & Polymers USA.

The name and logo INEOS are trademarks of the INEOS Group and its affiliated companies and businesses.

2600 South Shore Boulevard, Ste. 500
League City, TX 77573
Tel: 281-535-6600
www.ineos-op.com

INEOS
Olefins & Polymers USA

Manufacturer website: https://www.ineos.com/businesses/ineos-olefins-polymers/