Manufacturer website: https://www.irpc.co.th/en/

POLIMAXX

TECHNICAL DATA SHEET
REV20250623

B1101

Polypropylene Homopolymer / Extrusion Grade

PRODUCT DESCRIPTION

B1101 is a Homo-Polypropylene (Homo-PP), with low melt flow rate for using in extrusion blow molding and sheet extrusion process. The features are general purpose for vacuum and pressure forming. It's suitable for bottles, food trays, and etc.

INDUSTRY

- Extrusion Blow Molding
- Thermoforming Packaging
- Extrusion Sheet

PRODUCT FEATURE

- High Impact Strength
- High Stiffness
- Food contact

REGULATION COMPLIANCE

- FDA US 21 CFR 177.1520
- Commission Regulation (EU) No. 10/2011
- RoHS Directive 2011/65/EU
- REACH Regulation (EC) No. 1907/2006
- Halal

PHYSICAL PROPERTY	TEST METHOD	UNIT	VALUE
Melt Flow Rate (230°C/2.16 kg)	ASTM D 1238	g/10 min	0.9
Density (23°C)	ASTM D 792	g/cm^3	0.90
Mold Shrinkage	IRPC	%	0.7 - 1.5
MECHANICAL PROPERTY			
Tensile Strength at Yield (3.2 mm, 50 mm/min)	ASTM D 638	MPa	24
Flexural Modulus (1% Secant, 3.2 mm, 1.3 mm/min)	ASTM D 790	MPa	1600
Izod Notched Impact Strength (3.2 mm, 23 °C)	ASTM D 256	J/m	60
THERMAL PROPERTY (Unannealed)			
Heat Distortion Temperature (3.2 mm, 0.455 MPa)	ASTM D 648	°C	110

Conversion (1 MPa = 10.2 kgf/cm^2 | 1 J/m = 0.1 kgf-cm/cm)

Remark: The values presented above are typical laboratory, not to be construed as specifications and may vary within moderate ranges. The applicability or accuracy of this information or the suitability of our products cannot be guaranteed because users' conditions of use are beyond our control.

IRPC Public Company Limited | 555/2 Energy Complex, Building B, 6th Floor, Vibhavadi Rangsit Rd., Chatuchak, Bangkok 10900 THAILAND.
HTTPS://POLIMAXX.IRPC.CO.TH | TEL : +66(0) 765-7000

Manufacturer website: https://www.irpc.co.th/en/

Manufacturer website: https://www.irpc.co.th/en/

POLIMAXX

TECHNICAL DATA SHEET
REV20250623

B1101

Polypropylene Homopolymer / Extrusion Grade

PROCESSING TECHNIQUE

Cylinder Temperature	180 - 210 °C
Die Temperature	190 - 210 °C
Cooling Water Temperature	20 - 25 °C
Air Pressure	6 - 7 Bar

However, the actual processing conditions depend on machine design, power of machine, equipment and other environments.

PRODUCT PACKAGING

- 25 kg loose bag
- 25 kg stretch wrap on palletized
- 750 kg Jumbo bag

For further information, contact IRPC's Sales representative.

STORAGE

The resin should be stored in a dry location with good housekeeping practices during storage, transferring and handling. Process enclosures and adequate ventilation should be used to avoid excessive dust accumulation. Resin should be protected from direct sunlight, temperatures above 38°C (100°F) and high atmospheric humidity during storage. Higher storage temperatures may reduce the storage time. The container should be kept closed to prevent contamination. For the additional recommended storage conditions, please refer to SDS.

SAFETY

This product is not classified as hazardous material for more information please refer to safety data sheet.

RECYCLING

It is an undisputed fact that the product can be recycled or disposed of without any problem.

DISCLAIMER

The data indicated above are the results of IRPC's examinations, knowledge and correspond to the state of the art as of the date of publication and the data refers to the state of the related laws and regulations as of the date of issue. This information will expire after a break in delivery lasting more than 12 (twelve) months or in case of regulatory changes. This "Statement" is provided and subjected to IRPC's terms and conditions and IRPC reserves the right, in its sole discretion, to amend the product specification(s) at any time. This "Statement" is not intended and shall not be construed as specification, warranty, expressed or implied, or representation of any kind that IRPC would have any legal responsibility or liability. The applicability, accuracy, completeness, reliability, usability, availability, validity with respect to the data or information under this Statement and/or the suitability of IRPC's products cannot be guaranteed for any purpose. IRPC gives no guarantees or makes no warranties of any kind, express or implied, including, but not limited to, any warranties of merchantability, satisfactory quality, non-infringement or fitness for a particular purpose, whether arising by operation of law or otherwise. In the case that IRPC's products are used in combination with other materials, no liability admitted. When not utilized in combination with any third-party products, the information mentioned above refers only to IRPC's products. It is the customer's responsibility to inspect and test IRPC's products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer shall be responsible for the appropriate, safe and legal use, processing and handling of IRPC's products. IRPC shall not be liable for any false, inaccurate, inappropriate or incomplete data or information presented on this Statement. Please do not hesitate to ask IRPC for new information if needed. All terms and conditions regarding the supply of IRPC's products shall be subjected to IRPC's Policy. In the event that any dispute arises, IRPC's decision is final and not subject to appeal.

IRPC Public Company Limited | 555/2 Energy Complex, Building B, 6th Floor, Vibhavadi Rangsit Rd., Chatuchak, Bangkok 10900 THAILAND.
HTTPS://POLIMAXX.IRPC.CO.TH | TEL : +66(0) 765-7000

Manufacturer website: https://www.irpc.co.th/en/