DATASHEET

ASTM Property

Grade	SFI-841A
Product	Polypropylene, Random Terpolymer

General Information	
Key Features	- Low heat-seal temperature and wide hot-tack range. - Excellent transparency, glossiness and processibility. - Containing anti-blocking agent.
Applications	IOPP Film, Shrink Film (food packaging)

Item	Measuring Method	Unit	Value
Physical Properties			
Melt Flow Index (230℃, 2.16kg)	ASTM D1238	g/10min	5.5
Density	ASTM D792	g/㎤	0.9
Mechanical Properties			
Tensile Stress (Yield)	ASTM D638	kgf/㎠	190
Tensile Strain (Break)	ASTM D638	%	>500
Flexural Modulus	ASTM D790	kgf/㎠	6,500
Impact Properties			
Izod Impact Strength (notched, 23℃)	ASTM D256	kgf·㎝/㎝	10
Thermal Properties			
Melting Temperature	LC Method	℃	128
VICAT Softening Temperature	ASTM D1525	℃	111
Film Properties			
Haze	ASTM D1003	%	<1.5
Heat Seal Temperature	LC Method	℃	116

1. Physical Properties : these are not to be construed as specifications
2. Measured on 40 ㎛ mono-layer CPP film made of LOTTE CHEMICAL's cast film grade
3. ISO 9001, 14001, /TS 16949

* The last update date : 2024/11/06