Technical Data Sheet

# *Icorene* 5775 BUE 5503

High Density Polyethylene

## Product Description

*Icorene* 5775 is a high density polyethylene specifically developed for rotational moulding.This grade is particularly suitable for use in kayaks and boat applications. It has very high stifness and scratch resistance.

## Regulatory Status

For regulatory compliance information, see *Icorene* 5775 BUE 5503 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

| | |
|---|---|
| **Status** | Commercial: Active |
| **Availability** | Europe |
| **Processing Method** | Rotomolding |
| **Attribute** | Good Processability; High Scratch Resistance; Ultra High Stiffness; UV Resistant |
| **Forms** | Powder |
| **Appearance** | Natural Color; Unspecified Color |
| **Additive** | UV Stabilizer |
| **Application** | Water Sports Equipment |

| Typical Properties | Nominal Value | Units | Test Method |
|---|---|---|---|
| **Physical** | | | |
| Melt Flow Rate, (190 °C/2.16 kg) | 3.0 | g/10 min | ASTM D1238 |
| Density | 0.943 | g/cm³ | ASTM D1505 |
| **Mechanical** | | | |
| Tensile Strength at Yield | 21 | MPa | ASTM D638 |
| Flexural Modulus | 900 | MPa | ASTM D790 |
| Tensile Elongation at Break | 800 | % | ASTM D638 |
| **Impact** | | | |
| Drop Impact Resistance, (-20 °C, Internal Method) | 180 | J/cm | ASTM D4226 |
| **Hardness** | | | |
| Durometer Hardness, (Shore D) | 63 | | ASTM D2240 |
| **Thermal** | | | |
| Melting Temperature | 128 | °C | ASTM D2117 |



Manufacturer website: https://www.lyondellbasell.com/en/

## Notes

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2026

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.