Technical Data Sheet

Petrothene GA502119

Linear Low Density Polyethylene

Product Description

The *Petrothene* GA502 series of resins are pelletized linear low density polyethylenes for applications requiring excellent drawdown and toughness. These pelletized products offer excellent additive homogeneity, require no transfer equipment modification and facilitate clean and safe storage and handling. They can be used in either blown or cast film extrusion. GA502119 is formulated without TNPP.

Regulatory Status

For regulatory compliance information, see *Petrothene* GA502119 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

Status	Commercial: Not Promoted
Availability	North America
Application	Bags & Pouches; Can Liners; Colour Concentrates; Film Wrap; Food Packaging Film; Lamination Film; Liner Film; Stretch Wrap Film
Market	Flexible Packaging
Processing Method	Blown Film; Cast Film; Compounding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	2.0	g/10 min	2.0	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.918	g/cm³	0.918	g/cm³	ASTM D1505
Product Density, (23 °C)	0.918	g/cm³	0.918	g/cm³	ASTM D1505
Film					
Dart Drop Impact Strength, F50	120	g	120	g	ASTM D1709
Tensile Strength at Break					
MD	4900	psi	33.8	MPa	ASTM D882
TD	3600	psi	24.8	MPa	ASTM D882
Tensile Elongation at Break					
MD	750	%	750	%	ASTM D882
TD	800	%	800	%	ASTM D882
1% Secant Modulus					
MD	32000	psi	221	MPa	ASTM D882
TD	36000	psi	248	MPa	ASTM D882
Elmendorf Tear Strength					
MD	170	g	170	g	ASTM D1922
TD	400	g	400	g	ASTM D1922
Additive					
Slip	None		None		LYB Method
Antiblock	None		None		LYB Method

Manufacturer website: https://www.lyondellbasell.com/en/

Product	Product Density(g/cm³)	Slip(ppm)	Antiblock (ppm)
GA502022	0.923	1350	7000
GA502024	0.918	None	None
GA502119	0.918	None	None

Notes

Film sample used for testing was 1.5 mil gauge, 2.1:1 BUR.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.