Technical Data Sheet

Petrothene GA625189

Linear Low Density Polyethylene

Product Description

Petrothene GA625189 is a hexene LLDPE pelletized injection molding resin selected for use in applications requiring a balance of processability, ESCR, and low temperature toughness.

Regulatory Status

For regulatory compliance information, see *Petrothene* GA625189 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

Status	Commercial: Active
Availability	North America
Application	Caps & Closures
Market	Rigid Packaging
Processing Method	Injection Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	5.0	g/10 min	5.0	g/10 min	ASTM D1238
Density, (23 °C)	0.935	g/cm³	0.935	g/cm³	ASTM D1505
Mechanical					
Flexural Modulus					
(1% Secant)	105000	psi	725	MPa	ASTM D790
(2% Secant)	91000	psi	625	MPa	ASTM D790
Tensile Strength at Yield	2700	psi	18.6	MPa	ASTM D638
Environmental Stress Crack Resistance, F_{50} (100% Igepal®, Cond A)	>1000	hr	>1000	hr	ASTM D1693
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	131	°F	55	°C	ASTM D648
(264 psi, Unannealed)	102	°F	39	°C	ASTM D648

Manufacturer website: https://www.lyondellbasell.com/en/

Notes

Tensile properties were run with a crosshead speed of 2 inches/min or 50 mm/min.

Igepal® is a registered trademark of Rhodia.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.