Technical Data Sheet

Plexar PX3060

Tie-Layer, LLDPE

Product Description

Plexar tie-layers are chemically modified resins used to bond unlike materials, primarily in packaging and industrial applications. Common adherents include polyethylene resins and copolymers, EVA, EMA, polypropylene, polyamide (nylon), ethylene vinyl alcohol copolymers (EVOH), ionomer and other sealants, polyethylene terephthalate (PET) resins and copolymers, styrenic polymers, metal, and paperboard. Product grades primarily used for blown and cast films, sheet and thermoforming, blow molding, extrusion coating and lamination, tubing, pipe, and other specialty applications are available in pellet form. Contact your *Plexar* sales and/or Equistar technical service representative for more information and specific recommendations for your application(s).

Regulatory Status

For regulatory compliance information, see *Plexar* PX3060 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Australia and New Zealand; Europe; North America; South & Central America
Application	Barrier Film; Food Packaging Film
Market	Flexible Packaging; Tie-Layer
Processing Method	Blown Film

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	2.2	g/10 min	ASTM D1238
Density, (23 °C)	0.924	g/cm³	ASTM D1505
Film			
Tensile Strength at Break			
MD	30.1	MPa	ASTM D882
TD	23.9	MPa	ASTM D882
Tensile Strength at Yield			
MD	12.6	MPa	ASTM D882
TD	14.2	MPa	ASTM D882
Tensile Elongation at Break			
MD	760	%	ASTM D882
TD	760	%	ASTM D882
Tensile Elongation at Yield			
MD	16	%	ASTM D882
TD	10	%	ASTM D882
Elmendorf Tear Strength			
MD	117	g	ASTM D1922
TD	564	g	ASTM D1922
Water Vapor Transmission Rate, (38 °C, 100% RH) @ 2 mils	6.2	g/m²/day	ASTM F372

Manufacturer website: https://www.lyondellbasell.com/en/

Thermal			
Vicat Softening Point	100	°C	ASTM D1525

Notes

Film sample used for testing was 2.0 mil gauge, 2:1 BUR.

These are typical property values not to be construed as specification limits.

Processing Techniques

A process melt temperature above 410°F (210°C) is recommended to ensure adhesion between adherents.

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

Manufacturer website: https://www.lyondellbasell.com/en/