Technical Data Sheet

Moplen EP300M

Polypropylene, Impact Copolymer

Product Description

Moplen EP300M is a heterophasic copolymer for injection moulding . The product offers an excellent balance of stiffness, impact strength and processability. Typical applications fo *Moplen* EP300M are thin walled packaging, housewares and automotive parts.

Regulatory Status

For regulatory compliance information, see *Moplen* EP300M Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

Status	Commercial: Active
Availability	Africa-Middle East; Europe
Application	Crates; Housewares; Industrial
Market	Automotive; Compounding; Consumer Products; Rigid Packaging
Processing Method	Compounding; Injection Molding
Attribute	Good Impact Resistance; Good Processability; Good Stiffness

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	7	g/10 min	ISO 1133-1
Density	0.89	g/cm³	ISO 1183-1
Mechanical			
Flexural Modulus	1000	MPa	ISO 178
Tensile Modulus	900	MPa	ISO 527-1, -2
Tensile Stress at Break	17	MPa	ISO 527-1, -2
Tensile Stress at Yield	21.5	MPa	ISO 527-1, -2
Tensile Strain at Break	400	%	ISO 527-1, -2
Tensile Strain at Yield	7	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	45	kJ/m²	ISO 179
(0 °C)	9	kJ/m²	ISO 179
(-20 °C, Type 1, Edgewise, Notch A)	6	kJ/m²	ISO 179
Thermal			
Vicat Softening Temperature, (A50)	143	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	77	°C	ISO 75B-1, -2
DSC Melting Point	163	°C	DSC

Manufacturer website: https://www.lyondellbasell.com/en/

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.