Technical Data Sheet

Moplen EP5078

Polypropylene, Impact Copolymer

Product Description

Moplen EP5078 is a fractional melt flow heterophasic copolymer with very low gel and low odor, good stiffness impact balance, and good heat resistance. Typical customer applications are multilayer packaging, high heat resistance thermoforming tray, blow molding for cosmetic and detergent bottles, extrusion sheets with high gloss.

Regulatory Status

For regulatory compliance information, see *Moplen* EP5078 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Australia and New Zealand
Application	Bottles For Consumer Goods; General Sheet Extrusion; Opaque Containers; Thermoformed Food Containers
Market	Consumer Products; Rigid Packaging
Processing Method	Extrusion Blow Molding; Thermoforming
Attribute	High Gloss; High Heat Resistance; High Impact Resistance; Low Gel; Medium Rigidity

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	0.5	g/10 min	ASTM D1238
Density	0.90	g/cm³	ASTM D792
Mechanical			
Flexural Modulus	1400	MPa	ASTM D790
Tensile Strength at Yield	32	MPa	ASTM D638
Tensile Elongation at Yield	11	%	ASTM D638
Impact			
Notched Izod Impact Strength, (23 °C)	No Break		ASTM D256
Hardness			
Rockwell Hardness, (R-Scale)	98		ASTM D785
Thermal			
Vicat Softening Point	147	°C	ASTM D1525
Deflection Temperature Under Load, (0.46 N/mm²)	107	°C	ASTM D648

Manufacturer website: https://www.lyondellbasell.com/en/

Notes

These are typical property values not to be construed as specification limits.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.