Technical Data Sheet

Polyflam RIPP 4000 BLK70400

Polypropylene Copolymer

Product Description

Unfilled flame-retardant PP-Copolymer, halogenfree

Regulatory Status


For regulatory compliance information, see *Polyflam* RIPP 4000 BLK70400 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

Status	Commercial: Active
Availability	Europe
Processing Method	Injection Molding
Attribute	Copolymer; Good Processability; Halogen Free; UL Listed under File Numbers E86615 / E132739 / E31765
Additive	Flame Retardant
Resin ID	PP FR(40)

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Volume Flow Rate, (230 °C/2.16 kg)	13	cm³/10 min	ISO 1133
Density, (Method A)	1.05	g/cm³	ISO 1183
Mechanical			
Tensile Modulus, (1 mm/min, Type 1A)	2200	MPa	ISO 527-1
Tensile Strain at Yield, (Type 1A, 50 mm/min)	3.2	%	ISO 527-2
Nominal Tensile Strain at Break, (50 mm/min, Type 1A)	27	%	ISO 527-2
Tensile Stress at Yield, (Type 1A, 50 mm/min)	20.0	MPa	ISO 527-2
Tensile Stress at Break, (Type 1A, 50 mm/min)	15.7	MPa	ISO 527-2
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	4.0	kJ/m²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	2.3	kJ/m²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	55	kJ/m²	ISO 179
(-30 °C, Type 1, Edgewise)	16	kJ/m²	ISO 179
Thermal			
Vicat Softening Temperature			
(A (10N), 50 °C/h)	151	°C	ISO 306
(B (50N), 50 °C/h)	77.0	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa)	97	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	52.0	°C	ISO 75-2/A
Electrical			
Surface Resistivity	>1.0E+15	ohm	IEC 60093
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1

Manufacturer website: https://www.lyondellbasell.com/en/

Comparative Tracking Index (CTI)	600	V	IEC 60112
Flammable			
Burning Rate			
(2.00 mm, Self-Extinguishing)	0.0	mm/min	FMVSS 302
(2.00 mm, Self-Extinguishing)	0.0	mm/min	ISO 3795
Glow Wire Flammability Index			
(0.75 mm)	960	°C	IEC 60695-2-12
(1.5 mm)	960	°C	IEC 60695-2-12
(3.0 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			
(0.75 mm)	725	°C	IEC 60695-2-13
(1.5 mm)	725	°C	IEC 60695-2-13
(3.0 mm)	750	°C	IEC 60695-2-13
UL Information			
Flame Rating			
(0.75 mm)	V-0		UL 94
(1.5 mm)	V-0		UL 94
(3.0 mm)	5VA		UL 94
(3.0 mm)	V-0		UL 94
Flammability Classification			
(0.75 mm)	V-0		IEC 60695-11-10, -20
(1.5 mm)	V-0		IEC 60695-11-10, -20
(3.0 mm)	V-0		IEC 60695-11-10, -20
(3.0 mm)	5VA		IEC 60695-11-10, -20
UL File Number	E86615		



Injection Parameters	Nominal Value	Units
Drying Temperature	70 to 80	°C
Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	180 to 220	°C
Mold Temperature	40 to 80	°C
Screw Speed	<300	mm/sec
Holding Pressure	40.0 to 90.0	MPa

Manufacturer website: https://www.lyondellbasell.com/en/

Back Pressure	5.00 to 10.0	MPa
Injection Pressure	80.0 to 120	MPa
Injection Rate	Slow-Moderate	

Notes

These are typical property values not to be construed as specification limits.

Processing notes

Melt contacting surfaces should be made of a high quality, corrosive resistant steel. Positive experiences have been made with steel qualities containing > 12% chromium.

Avoid processing at very barrel high temperatures or above the recommended melt temperature range as this can increase risk of deposit onto the tool surfaces. Avoid long residence times. At start and end of production, it is recommended to purge clean with non-flame retardant polymer or a polyolefin.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.