Technical Data Sheet

Hostacom PF062-2 NA NATURAL

Polypropylene Compounds

Product Description

Hostacom PF062-2 NA NATURAL is a high melt flow, 4,500 MPa flexural modulus, chemically coupled, 20% glass fiber-reinforced polypropylene homopolymer that has good impact strength, high stiffness and very good moldfilling capability.

Regulatory Status

For regulatory compliance information, see *Hostacom* PF062-2 NA NATURAL Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

Status	Commercial: Active
Availability	North America
Application	Automotive Parts; Exterior Automotive Applications; Underhood
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ISO 1133-1
Density	1.04	g/cm³	ISO 1183-1
Mechanical			
Flexural Modulus, (23 °C)	4500	MPa	ISO 178
Tensile Stress at Yield	80	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	8.0	kJ/m²	ISO 180
Additional Information			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			

Manufacturer website: https://www.lyondellbasell.com/en/

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.