Technical Data Sheet

Metocene HM562S

Metallocene PP Homopolymer

Product Description

Metocene HM562S is a metallocene-catalyzed homopolymer with a very narrow molecular weight distribution, suitable for fiber extrusion application. It is formulated with an anti-gas fading stabilization package. It can be advantageously processed in different spinning technologies.

Typical applications are spunbond nonwovens and continuous filaments such as partially-oriented yarns(POY). Metocene HM562S expands processing capabilities to achieve unmatched properties balances. it allows faster spinning and lower denier filaments. Additional advantagesf of Metocene HM562S are low volatiles and low processing smokes.

Regulatory Status

For regulatory compliance information, see Metocene HM562S Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

Status	Commercial: Active
Availability	Africa-Middle East; Asia-Pacific; Australia and New Zealand
Application	Filament Yarn; Furniture & Buildings; Geotextile & Agriculture; Hygiene Nonwoven; Protective Clothes
Market	Textile
Processing Method	Continuous Filament/Spinning; Spunbond
Attribute	Controlled Rheology; Gas-fading Resistant; Homopolymer; Narrow Molecular Weight Distribution

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	30	g/10 min	ASTM D1238
Density	0.90	g/cm³	ASTM D792
Mechanical			
Flexural Modulus	1300	MPa	ASTM D790
Tensile Strength at Yield	32	MPa	ASTM D638
Tensile Elongation at Yield	10	%	ASTM D638
Impact			
Notched Izod Impact Strength, (23 °C)	30	J/m	ASTM D256
Hardness			
Rockwell Hardness, (R-Scale)	104		ASTM D785
Thermal			
Deflection Temperature Under Load, (0.46 N/mm²)	110	°C	ASTM D648

Manufacturer website: https://www.lyondellbasell.com/en/

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Users should determine the conditions necessary to obtain optimum product properties and suitability of the product for the intended application.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.