Technical Data Sheet

Pro-fax PF511

Polypropylene, Homopolymer

Product Description

Pro-fax PF511 radiation resistant, high melt flow, controlled rheology polypropylene homopolymer is available in pellet form. This resin is typically used in injection molding applications and offers enhanced retention of physical properties and color after radiation sterilization.

This resin resists yellowing and embrittlement after gamma radiation. However, since performance and appearance after radiation sterilization can be sensitive to design and processing choices, the users should verify performance in their application.

Our customers typically use this resin in applications such as medical devices, syringes, and labware.

Regulatory Status

For regulatory compliance information, see *Pro-fax* PF511 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

Status	Commercial
Availability	North America
Application	Labware; Medical Devices
Market	Healthcare
Processing Method	Injection Molding
Attribute	Good Processability; Radiation Resistant

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	20	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm³	0.90	g/cm³	ASTM D792
Mechanical					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	135000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			930	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	4000	psi			ASTM D638
(50 mm/min)			28	MPa	ASTM D638
Tensile Elongation at Yield	15	%	15	%	ASTM D638
Impact					
Notched Izod Impact Strength					
(73 °F, Method A)	0.6	ft-lb/in			ASTM D256
(23 °C, Method A)			32	J/m	ASTM D256
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	190	°F			ASTM D648
(0.45 MPa, Unannealed)			88	°C	ASTM D648

Manufacturer website: https://www.lyondellbasell.com/en/

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.