Technical Data Sheet

Pro-fax PH350

Polypropylene, Homopolymer

Product Description

Pro-fax PH350 general-purpose polypropylene homopolymer is available in spherical particle form. This resin has very minimal stabilization, which allows wide design latitude in compounding applications. Additional stabilization is required to protect the resin during melt processing and throughout its useful life.

Please note that any additives compounded into this resin will require a re-assessment of its FDA status.

Regulatory Status

For regulatory compliance information, see *Pro-fax* PH350 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

Status	Commercial: Active
Availability	North America
Application	Colour Concentrates; Polymer Modifier; Wood Composites
Market	Compounding
Processing Method	Compounding
Attribute	Dispersible; Good Stiffness; High Filler Loading Capability

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (230 °C/2.16 kg)	3.5	g/10 min	3.5	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm³	0.90	g/cm³	ASTM D792
Mechanical					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	200000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			1380	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	4800	psi			ASTM D638
(50 mm/min)			33	MPa	ASTM D638
Tensile Elongation at Yield	12	%	12	%	ASTM D638
Impact					
Notched Izod Impact Strength					
(73 °F, Method A)	1.0	ft-lb/in			ASTM D256
(23 °C, Method A)			53	J/m	ASTM D256
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	190	°F			ASTM D648
(0.45 MPa, Unannealed)			88	°C	ASTM D648

Manufacturer website: https://www.lyondellbasell.com/en/

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2026

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.