NOVA Chemicals
Polyethylene

Product Data Sheet

NOVAPOL® HB-W355-A Resin

Hexene Copolymer HDPE Blow Molding Resin

Property		ASTM (1)	Typical Values (2)			
High Load Melt Index	(3)	D 1238	3.0	g/10 min		
Density		D 792	0.955	g/cm³		
			METRIC UNITS		ENGLISH UNITS	
Molded Plaque Properties						
Yield Strength		D 638	28	MPa	4,100	psi
Elongation		D 638	820	%		
Flexural Modulus		D 790	1,380	MPa	200,200	psi
Low Temperature Brittleness Point		D 746	< -70	°C	< -94	°F
ESCR, (F_{50})	(4)	D 1693	> 500	h		
Izod Impact	(5)		7.8	J/cm	15	ft-lb/in

(1) Properties designated have been determined using methods which are in accordance with, or substantially in accordance with, the specified testing standards.

(2) Typical Values represent average laboratory values and are intended as guides only, not as specifications.

(3) Condition 190°C/21.6 kg.

(4) Environmental stress crack resistance, Condition B, 100% Igepal.

(5) 3.2 mm (0.125 in) thick specimen.

Melt Index	**3.0**
Density	**0.955**

Features

- High molecular weight
- Very high rigidity
- Excellent impact strength
- Excellent ESCR

Additives

- Process stabilizer

Applications

- Drums
- Large parts

Product Data Sheet

NOVA Chemicals Polyethylene

NOVAPOL HB-W355-A Resin

Hexene Copolymer HDPE Blow Molding Resin

Availability

NOVAPOL HB-W355-A polyethylene resins are available in bulk hopper cars, hopper trucks, boxes, sea bulk containers, or bags. The product type and batch number are clearly marked on each container. Contact the NOVA Chemicals sales office nearest you for availability in your area.

Storage/Handling

NOVAPOL HB-W355-A resin should be stored in a clean, dry place at ambient temperatures. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. The NOVA Chemicals Safety Data Sheet (SDS) contains important safety information and should be reviewed before using the product.

Processing Conditions

Comprehensive assistance with processing conditions and technology is available from NOVA Chemicals Technical Service at (403) 291-8444.

Environmental

NOVA Chemicals polyethylene resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of NOVA Chemicals' polyethylene resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact NOVA Chemicals Technical Service for further information on recycling and disposal of NOVA Chemicals resins.



is the SPI resin code developed for high density polyethylene to identify material type for sorting and recycling purposes.

The NOVA Chemicals logo is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.
NOVAPOL® is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.

The above information is provided in good faith. NOVA Chemicals is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, NOVA CHEMICALS MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.

June 18, 2026