Luban HP1102K
Polypropylene Homopolymer

Description

Luban polypropylene is manufactured using Novolen vertical stirred Gas-phase polymerization process. Luban HP1102K is a homopolymer polypropylene with low water carry over. The grade is designed for the production of films that can be converted into stretched tapes for weaving applications.

Application

Raffia, tapes and strapping.

Properties (Typical Values)

Property	Units	Test method	Value
Melt flow rate (230°C/2.16 kg)	g/10 min	ASTM D1238	3.4
Density	g /cm³	ASTM D792	0.90
Flexural Modulus (1% Secant)	MPa	ASTM D790	1500
Tensile Stress @ Yield	MPa	ASTM D638	37
Elongation @ Yield	%	ASTM D638	8
Tensile Stress @ Break	%	ASTM D638	20
Elongation @ Break (+23°C)	kJ/m²	ASTM D638	> 50
Notched Izod Impact Strength @23°C	kJ/m²	ASTM D256	35
Vicat Softening Temperature (10N)	°C	ASTM D1525	156
Heat Deflection Temperature (0.45 MPa)	°C	ASTM D648	100

Note: These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

Processing Guidlines

The Typical Processing Conditions for Luban HP1102K are:

Extrusion Temperatures	220 – 265 °C
Water Bath Temperature	35 – 45 °C
Orientation Temperatures Hot plate	100 – 140 °C
Hot rolls	100 – 140 °C
Oven air	140 – 160 °C
Draw Ratio	1:5 – 1:7

OQ head office
PO Box 261, PC 118
Muscat Grand Mall,
Muscat, Sultanate of Oman
www.oq.com

أوكيو المكتب الرئيسي
صندوق بريد ٢٦١، الرمز البريدي ١١
مسقط جراند مول
سلطنة عمان، مسقط
www.oq.com

Luban HP1102K
Polypropylene Homopolymer

Note: Processing parameters should only be used as guidelines. The above properties values are not to be construed as specifications.

Storage and Handling

Luban HP1102K must be protected from direct sunlight and should be stored in a shaded and completely dry area. During handling and processing, the material should be kept in a well-ventilated area to prevent the accumulation of dust and fumes. Contact with strong oxidizers, excessive heat, sparks or open flame should be avoided as this could initiate the degradation process and consequently impact the quality of the material.

Safety

Luban HP1102K is not classified as dangerous preparation. For further information about safety in handling and processing please refer to the Safety Data Sheet.

Food Contact

Luban HP1102K meets the requirements of the U.S. Food and Drug Administration (FDA) as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Product Stewardship Declaration".

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Updated: Feb. 2023

Disclaimer:
Values given here are typical and should not be interpreted as specification. Before using OQ product, customers and other users should make their own independent determination that the product is suitable for the intended use. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under OQ or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of OQ except in a writing signed by an authorized OQ employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at OQ's option, and in no event shall OQ be liable for special, consequential, incidental, punitive or exemplary damages.

OQ head office
PO Box 261, PC 118
Muscat Grand Mall,
Muscat, Sultanate of Oman
www.oq.com

أوكيو المكتب الرئيسي
صندوق بريد ٢٦١، الرمز البريدي ١١٨
مسقط جراند مول
سلطنة عمان، مسقط
www.oq.com