Technical Data Sheet

PETOPLEN PP EC261
Polypropylene (PP)

Description

PETOPLEN PP EC261 is a polyolefin product with a medium molecular weight distribution. It has been specially developed for extrusion coating applications.

Applications

Extrusion coating: Woven/non-woven PP fabrics, paper, cardboard.

Properties	Typical Values (*)	Units	Test Methods
Resin Properties			
Melt Flow Rate (230°C/2.16 kg)	26	g/10 min	ASTM D1238
Density	0.910	g/cm³	ASTM D792
Mechanical Properties			
Tensile Strength at Yield(**)	28	MPa	ASTM D638
Flexural Modulus, 23°C	900	MPa	TS EN ISO 178
Thermal Properties			
Vicat Softening Temperature A50 (10N)	129	°C	ISO 306

(*) These are typical properties only and are not to be construed as specifications. Customers should confirm results by their own tests.
(**) The values given are measured based on compression molded sheet.

PETKIM PETROCHEMICAL HOLDING INC.
Siteler Mah. Necmettin Giritlioğlu Cad.
SOCAR Türkiye Aliağa Yönetim Binası No: 6/1 35800 Aliağa/İZMİR
Tel: +90 232 616 12 40 www.petkim.com.tr

Manufacturer website: https://www.petkim.com.tr/

Technical Data Sheet

PETOPLEN PP EC261
Polypropylene (PP)

Recommended Processing Conditions

Extrusion coating applications;
Typical melt temperature: 270-300°C

Processing conditions should be optimized for different equipment design.

Health, Safety and Food Contact Regulations

The detailed information of the PETOPLEN PP EC261 product is given in Safety Data Sheet and Food Contact Declaration of the product. Please contact your sales representatives or visit web site for the food contact application compliance (e.g. EU, FDA) and other regulatory documents.

Packing and Storage

The product is packed in 25 kg PP Mesh Valve Bag or 900 kg PP Mesh Big-Bag. The product should be stored in a dry area with an ambient temperature below 50°C. It should be kept away from sunlight, sparks, heat and flame. Inappropriate storage conditions can lead to bad smell, color changes and the deterioration in physical properties. It is advised to process PP resins within 6 months after delivery. Prior to processing PP product bags shall be kept in production area for at least 12 hours.

Recycling

The product is not hazardous or toxic and it is suitable for recycling using available recycling methods.

Disclaimer

© 2025 PETKIM PETROCHEMICAL HOLDING INC. The user may photocopy, distribute and/or forward this document only if unaltered and complete including its headers, footers and other information. You may not publish this document on a website. PETKIM does not guarantee the typical values. The information in this document relates only to the given product when not in combined or compounded with any other materials. The information in this document is based on data reliable on the date compiled. PETKIM may add, remove and/or update information in this document at any time without noticing the users. PETKIM does not guarantee the merchantability, suitability, fitness for particular purpose, accuracy, reliability or completeness of this information or the products specified. The user is solely responsible for any use of the product at any process. PETKIM disclaims liability for any loss, damage or injury directly or indirectly suffered or incurred as a result or related to anyone using or relying on any information in this document.

PETKIM PETROCHEMICAL HOLDING INC.
Siteler Mah. Necmettin Giritlioğlu Cad.
SOCAR Türkiye Aliağa Yönetim Binası No: 6/1 35800 Aliağa/İZMİR
Tel: +90 232 616 12 40 www.petkim.com.tr

Manufacturer website: https://www.petkim.com.tr/