Product Data and Technical Information

POLYMER TYPE: Polypropylene Homopolymer Granule

GRADE NAME: RG 1001 P

APPLICATION: High stiffness injection moulded parts, special extrusion applications, compounding

PRODUCT FEATURES: Homopolymer with high stiffness and stabilization

PROCESSING METHOD: Extrusion

Property	Test Method	Unit	Value
MFR (230 ˚C/ 2.16 kg)	ASTM D1238/L	g/10min	14.6 – 16.5
Tensile Modulus of Elasticity (1 mm/min)	ASTM D638	MPa	2000
Tensile Strength at Yield (50 mm/min)	ASTM D638	MPa	40
Notched Charpy Impact at 23˚C	ISO 179/ 1eA	kJ/m^2	2.5
Vicat Softening Point, 10N	ASTM D1525	˚C	158
HDT (0.46 N/mm^2)	ASTM D648	˚C	110
Melting Point, DSC	ASTM D3417	˚C	163
Density	ASTM D792	g/cm^3	0.91

"The information in this publication is submitted without prejudice, and is based on our current knowledge and experience and on a limited number of tests.
In view of the many factors that may affect processing and application, these data do not relieve the receiver of this information from the responsibility of carrying out their own tests and experiments; neither do they imply and legally binding assurance of certain properties or of suitability for a specific purpose of the products made with or on the basis of the information in this publication."

Regal Petrochemical & Industrial Complex