Technical Data Sheet
Chemicals

REPSOL ISPLEN PM274AS

REPSOL ISPLEN PM274AS is a polypropylene copolymer, 20% mineral fillers reinforced and with high processability. It shows high stiffness and good impact strength. It gives good aesthetic properties and high gloss surface. The product has a standard stabilization, able to be used in the main applications.

Applications

- Automotive: insertion, steps, structural parts
- Electrical appliances and white line.
- Technical pieces, in general.

Recommended melt temperature range from 190 to 250ºC. Processing conditions should be optimized for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
GENERAL			
Melt flow rate (230°C/ 2,16 kg)	13.5	g/10 min	ISO 1133
Density at 23ºC	1060	kg/m^3	ISO 1183
MECHANICAL			
Flexural modulus of elasticity	2400	MPa	ISO 178
Tensile modulus of elasticity	2200	MPa	ISO 527
Tensile strength at break	21	MPa	ISO 527-2
Elongation at break	15	%	ISO 527-2
Tensile strength at yield	21	MPa	ISO 527-2
Elongation at yield	3	%	ISO 527-2
Charpy impact strength (23°C,notched)	5,5	kJ/m^2	ISO 179
Charpy impact strength (23°C,unnotched)	52	kJ/m^2	ISO 179
Charpy impact strength (0°C,notched)	2,5	kJ/m^2	ISO 179
Charpy impact strength (0°C,unnotched)	30	kJ/m^2	ISO 179
Charpy impact strength (-20°C,notched)	2	kJ/m^2	ISO 179
Charpy impact strength (-20°C,unnotched)	28	kJ/m^2	ISO 179
Charpy impact strength (-40°C,notched)	1,6	kJ/m^2	ISO 179
Charpy impact strength (-40°C,unnotched)	24	kJ/m^2	ISO 179
OTHER			
VIcat softening temperature A120 (10N)	150	ºC	ISO 306
VIcat softening temperature A120 (50N)	79	ºC	ISO 306
HDT 0,45 MPa	91	°C	ISO 75
HDT 1,8 MPa	59	°C	ISO 75
Shore Hardness D	65	-	ISO 868

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registeres desings cannot be assumed.

Technical Service and Development:
Repsol Technology Lab
Ctra. de Extremadura A5, Km 18
28931 Móstoles
Tel. +34 91 753 85 00
atd_poliolefinas@repsol.com

Headquarters
Méndez Álvaro, 44
28045 Madrid
España
www.repsol.com

Customer Care
sacrq@repsol.com

All our polyolefins are recyclable

Technical Data Sheet
Chemicals

Storage

REPSOL ISPLEN PM274AS be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60ºC and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and properties of the transformed product.

Disclaimer

This grade does not comply with the European regulations for materials for use in contact with food, nor is it intended to be used in medical, pharmaceutical, or health applications, so Repsol does not authorize its use in them.

Repsol does not grant express or implicit guarantees that extend beyond the description contained herein. Nothing herein shall constitute any guarantee of merchantability or fitness for a particular purpose. Before using a product sold by Repsol, users must make their own independent determination that the product is safe, legal, and technically suitable for its intended use. Repsol does not assume any responsibility for the use of its materials together with other materials.

Related documents

The following related documents are available on request, and represent various aspects on the usability and safety of the product:

- Safety data sheet

Recommended consumption period: 12 months from the raw material reception

July 2021

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registeres desings cannot be assumed.

Technical Service and Development:
Repsol Technology Lab
Ctra. de Extremadura A5, Km 18
28931 Móstoles
Tel. +34 91 753 85 00
atd_poliolefinas@repsol.com

Headquarters
Méndez Álvaro, 44
28045 Madrid
España
www.repsol.com

Customer Care
sacrq@repsol.com

All our polyolefins are recyclable