Technical Data Sheet
Chemicals

REPSOL

REPSOL ISPLEN PM281AV

REPSOL ISPLEN PM281AV is a polypropylene copolymer medium mineral filled and medium melt flow rate. It shows high stiffness and good impact resistance, low warpage and high shrinkage behavior. It shows outstanding gloss surface and excellent scratch resistance. The product is UV stabilized.

Applications

- Automotive: interior trims and panels.
- Electrical appliances.
- Technical pieces, in general.

Recommended melt temperature range from 190 to 250ºC. Processing conditions should be optimized for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
GENERAL			
Melt flow rate (230°C/ 2,16 kg)	26	g/10 min	ISO 1133
Density at 23ºC	1040	kg/m^3	ISO 1183
MECHANICAL			
Flexural modulus of elasticity	2600	MPa	ISO 178
Tensile modulus of elasticity	1900	MPa	ISO 527
Tensile strength at break	24	MPa	ISO 527-2
Elongation at break	12	%	ISO 527-2
Tensile strength at yield	28	MPa	ISO 527-2
Elongation at yield	4	%	ISO 527-2
Charpy impact strength (23°C,notched)	3	kJ/m^2	ISO 179
Charpy impact strength (23°C,unnotched)	95	kJ/m^2	ISO 179
Charpy impact strength (0°C,notched)	2,5	kJ/m^2	ISO 179
Charpy impact strength (0°C,unnotched)	52	kJ/m^2	ISO 179
Charpy impact strength (-30°C,notched)	1,5	kJ/m^2	ISO 179
Charpy impact strength (-30°C,unnotched)	35	kJ/m^2	ISO 179
Izod impact strength (23°C,notched)	5	kJ/m^2	ISO 180
Izod impact strength (-30°C,notched)	4	kJ/m^2	ISO 180
Izod impact strength (-30°C,unnotched)	19	kJ/m^2	ISO 180

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registeres desings cannot be assumed.

Technical Service and Development:
Repsol Technology Lab
Ctra. de Extremadura A5, Km 18
28931 Móstoles
Tel. +34 91 753 85 00
atd_poliolefinas@repsol.com

Headquarters
Méndez Álvaro, 44
28045 Madrid
España
www.repsol.com

Customer Care
sacrq@repsol.com

All our polyolefins are recyclable

Technical Data Sheet
Chemicals

OTHER			
VIcat softening temperature A120 (10N)	148	ºC	ISO 306
VIcat softening temperature A120 (50N)	80	ºC	ISO 306
HDT 0,45 MPa	111	°C	ISO 75
HDT 1,8 MPa	59	°C	ISO 75
Shrinkage, 150x100x3mm	0,82 – 0,85	%	ISO 2577
Shore Hardness D	65	-	ISO 868

Storage

REPSOL ISPLEN PM281AV be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60ºC and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and properties of the transformed product.

Disclaimer

This grade complies with the European regulations for materials for use in food contact. This grade is not intended to be used in medical, pharmaceutical, or healthcare applications, therefore Repsol does not authorize its use in them.

Repsol does not grant express or implicit guarantees that extend beyond the description contained herein. Nothing herein shall constitute any guarantee of merchantability or fitness for a particular purpose. Before using a product sold by Repsol, users must make their own independent determination that the product is safe, legal, and technically suitable for its intended use. Repsol does not assume any responsibility for the use of its materials together with other materials.

Related documents

The following related documents are available on request, and represent various aspects on the usability and safety of the product:

- Safety data sheet
- Statement on compliance with food contact regulations

Recommended consumption period: 12 months from the raw material reception

July 2021

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registeres desings cannot be assumed.

Technical Service and Development:
Repsol Technology Lab
Ctra. de Extremadura A5, Km 18
28931 Móstoles
Tel. +34 91 753 85 00
atd_poliolefinas@repsol.com

Headquarters
Méndez Álvaro, 44
28045 Madrid
España
www.repsol.com

Customer Care
sacrq@repsol.com

All our polyolefins are recyclable