Technical Data Sheet
Chemicals

REPSOL ISPLEN PM281BV

REPSOL ISPLEN PM281BV is a polypropylene copolymer, 20% mineral fillers reinforced and good melt flow rate. It was designed showing a high stiffness with a good impact resistance, and a low warpage and high shrinkage behaviour. It shows really good gloss surface and an excellent scratch resistance. The product is UV stabilized.

Applications

- Automotive: interior trims and panels.
- Electrical appliances.
- Technical pieces, in general.

Recommended melt temperature range from 190 to 250ºC. Processing conditions should be optimized for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
GENERAL			
Melt flow rate (230°C/ 2.16 kg)	18	g/10 min	ISO 1133
Density at 23ºC	1035	kg/m^3	ISO 1183
MECHANICAL			
Flexural modulus of elasticity	2300	MPa	ISO 178
Charpy impact strength (23°C, notched)	4	kJ/m^2	ISO 179
Charpy impact strength (-20°C, notched)	2.5	kJ/m^2	ISO 179
Izod impact strength (23°C, notched)	4.5	kJ/m^2	ISO 180
Izod impact strength (-20°C, notched)	3	kJ/m^2	ISO 180
OTHER			
HDT 0,.45 MPa	106	°C	ISO 75

Storage

REPSOL ISPLEN PM281BV be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60ºC and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and properties of the transformed product.

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registeres desings cannot be assumed.

Technical Service and Development:
Repsol Technology Lab
Ctra. de Extremadura A5, Km 18
28931 Móstoles
Tel. +34 91 753 85 00
atd_poliolefinas@repsol.com

Headquarters
Méndez Álvaro, 44
28045 Madrid
España
www.repsol.com

Customer Care
sacrq@repsol.com

All our polyolefins are recyclable

Technical Data Sheet
Chemicals

Disclaimer

This grade does not comply with the European regulations for materials for use in contact with food, nor is it intended to be used in medical, pharmaceutical, or health applications, so Repsol does not authorize its use in them.

Repsol does not grant express or implicit guarantees that extend beyond the description contained herein. Nothing herein shall constitute any guarantee of merchantability or fitness for a particular purpose. Before using a product sold by Repsol, users must make their own independent determination that the product is safe, legal, and technically suitable for its intended use. Repsol does not assume any responsibility for the use of its materials together with other materials.

Related documents

The following related documents are available on request, and represent various aspects on the usability and safety of the product:

- Safety data sheet

Recommended consumption period: 12 months from the raw material reception

September 2022

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registeres desings cannot be assumed.

Technical Service and Development:
Repsol Technology Lab
Ctra. de Extremadura A5, Km 18
28931 Móstoles
Tel. +34 91 753 85 00
atd_poliolefinas@repsol.com

Headquarters
Méndez Álvaro, 44
28045 Madrid
España
www.repsol.com

Customer Care
sacrq@repsol.com

All our polyolefins are recyclable