Technical Data Sheet
Chemicals

REPSOL ISPLEN PM360AT

REPSOL ISPLEN PM360AT is a polypropylene homopolymer high mineral filled and good melt flow rate. It gives a good compromise between stiffness and impact strength, a low warpage and shrinkage behavior. This product is high heat stabilized.

Applications

- Automotive: Under the bonnet parts subjected to high thermal stress (Light housings, heat and ventilation ducts), air conditioning elements inside the car
- White goods: components in washing machines.
- Technical pieces, in general.

Recommended melt temperature range from 190 to 250ºC. Processing conditions should be optimized for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
GENERAL			
Melt flow rate (230°C/ 2,16 kg)	9	g/10 min	ISO 1133
Density at 23ºC	1140	kg/m^3	ISO 1183
MECHANICAL			
Flexural modulus of elasticity	3500	MPa	ISO 178
Izod impact strength (23°C,notched)	2,25	kJ/m^2	ISO 180
Izod impact strength (-20°C,notched)	1,6	kJ/m^2	ISO 180
Charpy impact strength (23°C,notched)	2,5	kJ/m^2	ISO 179
OTHER			
HDT 0,45 MPa	119	°C	ISO 75

Storage

REPSOL ISPLEN PM360AT be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60ºC and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and properties of the transformed product.

Disclaimer

This grade does not comply with the European regulations for materials for use in contact with food, nor is it intended to be used in medical, pharmaceutical, or health applications, so Repsol does not authorize its use in them.

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registeres desings cannot be assumed.

Technical Service and Development:
Repsol Technology Lab
Ctra. de Extremadura A5, Km 18
28931 Móstoles
Tel. +34 91 753 85 00
atd_poliolefinas@repsol.com

Headquarters
Méndez Álvaro, 44
28045 Madrid
España
www.repsol.com

Customer Care
sacrq@repsol.com

All our polyolefins are recyclable

Technical Data Sheet
Chemicals

Repsol does not grant express or implicit guarantees that extend beyond the description contained herein. Nothing herein shall constitute any guarantee of merchantability or fitness for a particular purpose. Before using a product sold by Repsol, users must make their own independent determination that the product is safe, legal, and technically suitable for its intended use. Repsol does not assume any responsibility for the use of its materials together with other materials.

Related documents

The following related documents are available on request, and represent various aspects on the usability and safety of the product:

- Safety data sheet

Recommended consumption period: 12 months from the raw material reception

October 2022

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registeres desings cannot be assumed.

Technical Service and Development:
Repsol Technology Lab
Ctra. de Extremadura A5, Km 18
28931 Móstoles
Tel. +34 91 753 85 00
atd_poliolefinas@repsol.com

Headquarters
Méndez Álvaro, 44
28045 Madrid
España
www.repsol.com

Customer Care
sacrq@repsol.com

All our polyolefins are recyclable