TECHNICAL DATA SHEET

Repsol Isplen® PR264M1F

The grade REPSOL ISPLEN PR264M1F is a phthalate free polypropylene random copolymer designed for cast film applications. It is suitable for the manufacturing of non-oriented films with high transparency and good heat-sealability.

This grade is formulated with slip (1600 ppm) and antiblocking (1600 ppm) agents to provide the film with the best processability in high-speed transformation equipment.

Applications:

Extrusion and/or co- extrusion of non-oriented film, such a cast film or tubular quench, addressed to:

- Food packaging
- Lamination film
- Stationery film
- Flower packaging
- Textile packaging

Recommended melt temperature range from 190 to 230°C. Processing conditions should be optimized for each production line.

Properties:

Properties	Value	Unit	Test Method
General			
Melt flow rate (230°C/2.16 kg)	8.5	g/10 min	ISO 1133
Density at 23°C	905	kg/m^3	ISO 1183
Mechanical			
Flexural Modulus	900	MPa	ISO 178
Charpy impact strength (23°C, notched)	6	kJ/m^2	ISO 179
Other			
VICAT, 10N	130	°C	ISO 306
HDT 0.45 MPa	55	°C	ISO 75

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designs cannot be assumed.

Technical Service & Development:
Tel. +34 91 753 86 00
ATD_Polimeros@repsol.com

Headquarters
Méndez Álvaro, 44
28045 Madrid
España
www.repsol.com

Customer Care
CustomerCare.materials@repsol.com

TECHNICAL DATA SHEET

Storage:

REPSOL ISPLEN PR264M1F should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60ºC and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and properties of the transformed product.

Disclaimer:

This grade complies with the European regulations for materials for use in food contact. This grade is not intended to be used in medical, pharmaceutical, or healthcare applications, therefore Repsol does not authorize its use in them.

Repsol does not grant express or implicit guarantees that extend beyond the description contained herein. Nothing herein shall constitute any guarantee of merchantability or fitness for a particular purpose. Before using a product sold by Repsol, users must make their own independent determination that the product is safe, legal, and technically suitable for its intended use. Repsol does not assume any responsibility for the use of its materials together with other materials.

Related documents:

The following related documents are available on request, and represent various aspects on the usability and safety of the product:

- Safety data sheet.
- Statement on compliance with food contact regulations.

Recommended consumption period: 12 months from the date of delivery to the customer.

June 2026

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designs cannot be assumed.

Technical Service & Development:
Tel. +34 91 753 86 00
ATD_Polimeros@repsol.com

Headquarters
Méndez Álvaro, 44
28045 Madrid
España
www.repsol.com

Customer Care
CustomerCare.materials@repsol.com