Technical Data Sheet

Product Name
SCGC™ HDPE COMPOUND

Product Type
PE100 Blue HDPE Compound

Product Grade
H1000PBL

Product Description

SCGC™ HDPE H1000PBL is a blue (no lighter than RAL 5005), trimodal, high density polyethylene compound that is specially designed for water pressure pipe, especially for drinking water pipe. SCGC™ HDPE H1000PBL is designed as PE100 pipe providing excellent in mechanical properties, and processablitiy. Well dispersed UV stabilizer and anti-oxidant which also provide outstanding UV resistance and high thermal stability for long term using.

Typical Application

- Drinking water pipes
- Stripe and jacketing for PE100 pipe

Product Characteristics

- Good process ability
- Good weathering resistance
- Outstanding mechanical strength
- Resistance to rapid crack propagation

Physical Properties

Properties	Test Method	Typical Value	Unit
Melt Flow Rate at 190 °C and 5.0 kg	ISO 1133	0.18	g/10 min
Density	ISO 1183	0.950	g/cm³
Tensile Strength at Yield (100 mm/min)	ISO 527	23	MPa
Tensile Strength at Break (100 mm/min)	ISO 527	> 30	MPa
Elongation at Break (100 mm/min)	ISO 527	> 600	%
Oxidative induction time at 210°C	ISO 11357	≥ 40	min
Pigment dispersion	ISO 18553	≤ 3	Rating
Flexural Modulus	ASTM D 790	1000	MPa
MRS classification	ISO 12162/ISO 9080	10	MPa
Resistance to slow crack growth at 80°C	ISO 13479	≥ 500	hrs
Rapid crack propagation Pc, S4	ISO 13477	≥ 10	bar

Note:
- The given values are typical value measured on the product. Values herein are not to be constructed as a product specification.
- Conversion factor for changing unit from kg/cm^2 to MPa is divided by 10.20.

Thai Polyethylene Co., Ltd.
1 Siam Cement Road, Bangsue, Bangkok, 10800 Thailand
E-mail: pipe_compound@scg.com

Manufacturer website: https://www.scgchemicals.com/en

Technical Data Sheet

Product Name
SCGC™ HDPE COMPOUND

Product Type
PE100 Blue HDPE Compound

Product Grade
H1000PBL

Processing Guidelines

For extrusion of SCGC™ HDPE H1000PBL, it is recommended to use a screw equipped with suitable mixing screw elements in order to achieve pigment dispersion.

For normal extrusion equipment, we suggest a melt temperature of 200 – 220 °C, and drying 80 – 90 °C for 1 - 2 hours before use.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, contact your SCG Chemicals technical services at the address as specified below.

Product Available Form

- Pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Sea bulk container

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Co., Ltd.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Chemicals technical services.

Thai Polyethylene Co., Ltd.
1 Siam Cement Road, Bangsue, Bangkok, 10800 Thailand
E-mail: pipe_compound@scg.com

Manufacturer website: https://www.scgchemicals.com/en

	Technical Data Sheet	Product Name **SCGC™ HDPE COMPOUND**
	Product Type **PE100 Blue HDPE Compound**	Product Grade **H1000PBL**

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Chemicals technical services.

Related Documents

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Chemicals technical services.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
  - Safety Data Sheet
  - Declaration of Compliance

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.