TotalEnergies

TotalEnergies Petrochemicals & Refining USA, Inc.
Polymers Americas

Polypropylene 3721WZ

Technical Data Sheet
Polypropylene – Homopolymer
Produced in the United States

Description

Polypropylene 3721WZ is designed with high flow characteristics for ease of filling thin wall parts.

Antistat: 3721WZ is engineered with a high level of antistat for shelf cleanliness and mold release.

FDA: 3721WZ complies with all applicable FDA regulations for food contact applications.

Nucleation: 3721WZ is nucleated to provide fast cycle time and improve contact clarity in thin wall, multi-cavity molds.

Applications: 3721WZ is ideal for caps, closures, cutlery, and other thin wall multi-cavity applications.

Processing: 3721WZ processes on conventional injection molding equipment with typical melt temperatures of 390°F-450°F (200°C-232°C).

Characteristics

	Method	Unit	Typical Value
Rheological Properties			
Melt Flow	D-1238	g/10 min	20
Mechanical Properties			
Tensile Strength @ Yield	D-638	psi (MPa)	5,500 (38)
Tensile Elongation @ Yield	D-638	%	12
Tensile Modulus	D-638	psi (MPa)	260,000 (1,795)
Flexural Modulus	D-790	psi (MPa)	270,000 (1,860)
Izod Impact @ 73°F Notched Unnotched	D-256A	ft-lb/in (J/m)	 0.5 (27) 20.0 (1,068)
Hardness	D-785A	Rockwell R	107
Thermal Properties(1)			
Melting Point	DSC(2)	°F (°C)	330 (165)
Heat Deflection	D-648	°F @ 66 psi °C @ 4.64 kg/cm^2	260 127
Other Physical Properties			
Density	D-1505	g/cc	0.905

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.
(2) MP determined with a DSC-2 Differential Scanning Calorimeter. Test procedure available upon request.

Rev: Feb 2026

TOTALENERGIES PETROCHEMICALS & REFINING USA, INC.
POLYMERS AMERICAS
1201 Louisiana Street
Suite 1800
Houston, TX 77002
www.polymers.totalenergies.com

TECHNICAL CENTER
P.O. Box 1200
Deer Park, Texas 77536
Phone: 281-884-7500

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TotalEnergies products must be guided by the users own methods for selection of proper formulation. TotalEnergies Petrochemicals & Refining USA Inc. disclaims any responsibility for misuse or misapplication of its products. TotalEnergies MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TotalEnergies' liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.